Clays and Clay Minerals, Vol. 23, p. 167. Pergamon Press 1975. Printed in Great Britain

ANNOUNCEMENT

PREPARATION OF TABLES

Authors are advised that in future tables will be directly reproduced by the printer and not type-set. This will materially reduce costs of publication and hopefully reduce delays. The guidelines detailed below should be followed:

1. Page size should be $5\frac{3}{4} \times 9\frac{1}{4}$ inches (or 14·5 × 23·5 cm).
2. Large or long tables should be typed on continuing sheets.
3. Table headings should be typed on separate sheets, but identifying numbers should be placed on the upper right-hand corner of each sheet of tabular material.
4. Footnotes should be typed on separate sheets.
5. Original typed tables are required.

It will be the author's responsibility to prepare his tables in accordance with this procedure, as no facilities exist at the Editorial Office for retyping.

NEWS

ANNUAL SUSTAINING MEMBERS OF THE CLAY MINERALS SOCIETY

Amoco Production Company
Anglo-American Clays Corporation
Babcock and Wilcox Company
Freeport Kaolin Company
General Refractories Company
Georgia Kaolin Company
A. P. Green Refractories Company
Halliburton Company
J. M. Huber Corporation, Clay Division
Magcobar Operations, Dresser Industries
Marathon Oil Company
Thiele Kaolin Company
Union Oil Company of California
United Sierra Division, Cyprus Mines Corporation

https://doi.org/10.1346/CCMN.1975.0230219 Published online by Cambridge University Press